

**Gloss level measured on glass at an angle 60° (the varnish is applied with a wet coat thickness of 120 µm)**

<b>TOP COAT</b>	<b>UNITS</b>
<b>IRSA Platinum 3000 silky matt</b>	<b>40 - 44</b>
<b>IRSA Platinum 3000 ultra matt</b>	<b>16 - 21</b>
<b>IRSA Platinum 3001 silky matt</b>	<b>41 - 48</b>
<b>IRSA Platinum 2C PWL 3010 silky mat</b>	<b>35 - 43</b>
<b>IRSA Platinum 2C PWL 3030 ultra mat</b>	<b>15 - 20</b>
<b>IRSA Platinum 2C PWL 3055 high gloss</b>	<b>*</b>
<b>IRSA Holzsigel 2010 silky mat</b>	<b>20 - 28</b>

\* no data available

Status from 02/2010