



Lackfabrik Irmgard Sallinger GmbH

Technical Data Sheet

03/2022

## IRSA PLATINUM ISO-HÄRTER extrem-matt (Hardener) Component for IRSA PLATINUM 2K Nature Feeling extrem-matt (water-based varnish)

### Basic:

IRSA PLATINUM ISO-Härter extrem-matt is a ready-to-use hardener-component, available for IRSA PLATINUM 2K Nature Feeling extrem-matt.

**Caution:** IRSA PLATINUM ISO-Härter extrem-matt is for use only by professionals exclusively. Avoid contact with skin and wear protective gloves. Do not inhale aerosol-fog and wear mask while spraying.

### Ratio of Components = 20:1

**20 parts** of IRSA PLATINUM 2K Nature Feeling extrem-matt : **1 part** of IRSA PLATINUM ISO-Härter extrem-matt.

Mix 0,225 l of IRSA PLATINUM ISO-Härter extrem-matt into 4,5 l of IRSA PLATINUM 2K Nature Feeling extrem-matt or mix 0,45 l of IRSA PLATINUM ISO-Härter extrem-matt into 9,0 l of IRSA PLATINUM 2K Nature Feeling extrem-matt.

### Processing:

Fill the IRSA PLATINUM ISO-Härter extrem-matt into the can of IRSA PLATINUM 2K Nature Feeling extrem-matt and shake very well for at least 15 sec before use.

### Pot Life:

Work up the mixture of IRSA PLATINUM 2K Nature Feeling extrem-matt + IRSA PLATINUM ISO-Härter extrem-matt **within 2 hours** (keep part of the mixture in a closed container if not worked up within time).

### Temperature of Processing:

Room-climate/subsurface and varnish-hardener mixture not below +15°C, not over +30°C and not over 55% of relative air-humidity.

### Storage:

Keep cool and dry (store and transport not under +6°C and not above +30°C). Keep container tightly closed. Shelf life of unopened original container at least 12 months. Keep opened container tightly closed and work up soon. **Protect from cold!**

The IRSA PLATINUM ISO-Härter extrem-matt becomes useless by contact with water or dampness (material thickens).

Please, follow the caution marks on the IRSA PLATINUM ISO-Härter extrem-matt-Label.

### VOC-identification for 2007/2010; in ratio of 20:1

IRSA PLATINUM 2K Nature Feeling extrem-matt with IRSA PLATINUM Härter:2004/42/2 A(j) 140g/l <65g/l

2004/42	year and number of EU-guidelines
/2	addition 2
A	part A
()	product sub-category
---,---g/l	limit value in g/l
< ---g/l	current VOC-value

The advice given by us in word, writing and endeavour for the technical application is supplied to our best knowledge, but may, however, only be regarded as an indication without any obligation and does not exempt you from examining the supplied products yourself, if they are suitable for the procedure and purposes intended. Application, use and processing of the products are not within our range of control and supervision, but are at your responsibility exclusively. It goes without saying that we guarantee products of high and good quality, according to the samples. With the publishing of new information the earlier technical data sheets loose validity.